

Thermal properties of selected (co-)polymers

Polymer	Tg	Tm
RESOMER® L 206 S	60 - 65 °C	180 - 185 °C
RESOMER® L 207 S	60 - 65 °C	180 - 185 °C
RESOMER® L 209 S	60 - 65 °C	180 - 185 °C
RESOMER® L 210	60 - 65 °C	180 - 185 °C
RESOMER® L 210 S	60 - 65 °C	180 - 185 °C
RESOMER® LR 704 S	56 - 62 °C	amorphous
RESOMER® LR 706 S	56 - 62 °C	amorphous
RESOMER® LR 708	56 - 62 °C	amorphous
RESOMER® LC 703 S	32 - 42 °C	amorphous
RESOMER® LG 824 S	54 - 60 °C	amorphous
RESOMER® LG 857 S	57 - 63 °C	amorphous
RESOMER® RG 509 S	46 - 52 °C	amorphous
RESOMER® RG 502 / H	42 - 46 °C	amorphous
RESOMER® RG 503 / H	44 - 48 °C	amorphous
RESOMER® RG 504 / H	46 - 50 °C	amorphous
RESOMER® R 202 S	38 - 42 °C	amorphous
RESOMER® R 202 H	46 - 50 °C	amorphous
RESOMER® R 203 S	46 - 50 °C	amorphous
RESOMER® R 203 H	48 - 52 °C	amorphous
RESOMER® RG 752 S	44 - 50 °C	amorphous
RESOMER® RG 753 S	44 - 50 °C	amorphous
RESOMER® RG 755 S	48 - 54 °C	amorphous
RESOMER® RG 756 S	49 - 55 °C	amorphous